

Star Trek replicators and diatom nanotechnology

Ryan W. Drum¹ and Richard Gordon²

¹Island Herbs (Wildcraft Medicinal Herbs), Waldron Island, WA 98297 USA

²Departments of Radiology and Electrical & Computer Engineering, University of Manitoba, Room GA216, Health Sciences Centre, 820 Sherbrook Street, Winnipeg, MB R3A 1R9 Canada

Diatoms are single celled algae, the 10^5 – 10^6 species of which create a wide variety of three-dimensional amorphous silica shells. If we could get them to produce useful structures, perhaps by compustat selection experiments (i.e. forced evolution of development or evodevo), their exponential growth in suspension cultures could compete with the lithography techniques of present day nanotechnology, which have limited 3D capabilities. Alternatively, their fine detail could be used for templates for MEMS (micro electro mechanical systems), or their silica deposition systems isolated for guiding silica deposition. A recent paper has demonstrated that silica can be replaced atom for atom without change of shape – a step towards the Star Trek replicator.

Given that diatoms are responsible for ~25% of the world's net primary production [1] they have been the most underfunded organism per unit mass. This might be about to change with a flurry of activity in a new field dubbed 'diatom nanotechnology', which will have its debut in a workshop at the next North American Diatom Society Meeting, (see <http://serc.fiu.edu/periphyton/NADS/Homepage.html> and the forthcoming special issue of *J. Nanosci. Nanotech.*).

Paid and unpaid (so-called 'amateur') diatomists have spent lifetimes doing research on these single-celled creatures, with perhaps one universal motivation: they

are beautiful to behold (Figs 1a–c and Fig. 2). Some investigators got carried away, producing art only visible through a microscope, made of arrays of diatom valves (see <http://thalassa.gso.uri.edu/flora/arranged.htm>).

Diatom motility

At first, diatoms were thought to be animals (A.P. Ussing *et al.*, in preparation) because what are now called raphid diatoms move at speeds of up to $25 \mu\text{m s}^{-1}$ when attached to surfaces. They do this with no moving parts, although a 'raphe fluid' is exuded. A slow moving debate has occurred over three decades as to whether the motive force for diatom gliding motility is in the hydration and capillarity of the raphe fluid [2] controlled by actin [3], or whether actin provides the motive force [4]. A model for myxobacterium motility identical to the capillarity model for diatoms has been proposed [5], as well as a similar one for cyanobacterial gliding motility [6] (common ancestor or convergent evolution?). Furthermore, some diatoms use 'nozzles' (pore openings) analogous to those on myxobacteria, to secrete an adhesive material [7], which involves transient motility [8]. Definitive experiments are needed because control of the diatom motor, which can reverse rapidly 'on a dime', somehow detecting a collision or a change in light [9], is a fascinating problem of potentially universal significance. Control of motility of diatoms in rigid [10] shells would appear to be simpler than crawling of flexible tissue culture cells of ever-changing shape, and





Fig. 1. (a) Scanning electron micrograph (SEM) of the inside of one valve (shell) of the pennate diatom *Nitzschia* sp. about $20 \mu\text{m}$ long (see <http://www.bgsu.edu/departments/biology/facilities/algae/SEM/nitz1.gif>, with permission granted by Rex L. Lowe, Center for Algal Microscopy and Image Digitization, Bowling Green State University, OH, USA). The cross ribs form perpendicular to the long midrib, and if caught early by silica starvation, could remain as a comb. Most other pennates are approximately left–right symmetric. Note the pores, which form last. (b) Chain diatoms, *Bidulphia bidulphiana* (top) and *Odontella aurita*; scale bar $200 \mu\text{m}$. (c) Triangular diatoms, *Trigonium arcticum*; scale bar $100 \mu\text{m}$. (b,c) Taken from Point Loma, CA, USA and provided courtesy of Mary Ann Tiffany, Center for Inland Waters, San Diego State University, CA, USA). (d) Scanned electron micrograph of dry-ashed leaf of 'coronivia grass' *Brachiaria humicola* showing its silica bodies; scale bar $20 \mu\text{m}$ (permission of Christian Mulder, Paleobotany and Palynology, Utrecht University, The Netherlands).



TRENDS in Biotechnology

Fig. 2. Pairs of scanning electron micrographs (SEMs) showing marine centric diatoms and close-ups of surface features, courtesy of Mary Ann Tiffany. (a,b) *Glyphodiscus stellatus*, a very rare diatom from Mission Bay, San Diego, CA, USA (taken June 11, 2002); scale bar on the whole valve is 20 μm , on the close-up is 5 μm . (c,d) *Cyclotella meneghiniana* with asymmetric central buckling; scale bar 20 μm , close-up at 5 μm . For (c), radially oriented microtubules might provide a 'prepattern' for diffusion limited aggregation [41], a compromise between the two morphogenesis hypotheses. (e,f) *Roperia tessellata* taken 5 km off San Diego; the first scale bar is 10 μm and the scale bar on the close-up is 5 μm . (g,h) *Isthmia nervosa* from Providence Bay, Whidbey Island, Washington State, WA, USA) off red seaweed; scale bars are 50 μm and 1 μm .

thus a possible key to eukaryotic cell behavior. Given that diatoms move on surfaces, we could try to use patterned surfaces [11] to guide them into place, perhaps moved along by phototropism or geotropism [12,13], where they could become nanotechnology components.

In the remarkable colonial diatom *Bacillaria paradoxa* the cells move rhythmically against each other [1,14] (also A.P. Ussing *et al.*, in preparation), like a deck of cards sliding back and forth. (For an online movie see <http://thalassa.gso.uri.edu/plankton/theater/alphabetical.htm>). Because the velocities are additive, this is the world's fastest microorganism.

Diatom morphogenesis

Diatom shells are composed of amorphous silica [15] but are highly structured. They are basically made of hydrated glass: $\text{SiO}_2 \cdot n \text{H}_2\text{O}$. There are $10^5 - 10^6$ species of diatoms, distinguished by their shells [16]. How does an amorphous substance produce such a variety of organized shapes? Two major approaches have been followed: either the pattern forms spontaneously out of silica by diffusion limited aggregation (DLA) or there is a prepattern of something else onto which or within which the silica precipitates (which begs the question as to what causes that pattern) [17,18]. Neither approach has seriously invoked the genetics of diatoms, so there is a lot of work ahead. Although diatoms might not tell us how legs and arms and brains of vertebrates are put together, bridging the intellectual gap from the genome (now being sequenced in diatoms [19]) to diatom shell structure would be a great accomplishment. Intermediaries that have been discovered are the silica binding polyamines and silaffins [20]. Diatom DNA synthesis is silica dependent [21] and a silica membrane transport system exists [22]. Whether these

catalyze its (fractal) DLA precipitation, or somehow form a prepattern onto which silica precipitates, has yet to be determined. They probably account for the 20–40% organic content of diatom silica [17,18].

The big question, which is also fundamental to debates in evodevo (evolution and development), is whether diatoms (or any organisms) vary 'infinitely', or are subject to 'developmental constraints'. Fortunately, we can speed up evolution in the lab, especially for microorganisms, using mutagenic chemicals or ultraviolet light, and assorted methods for selecting those mutants that do best under conditions set. A classical device is the chemostat, which acts similarly to an artificial stomach for microorganisms to grow in: those that grow too slowly are washed out. It thus selects for speed of growth, amongst those mutants that can use the nutrients that are placed in the incoming medium. A variant of this idea is the compustat [23], in which a computer decides 'who shall live and who shall die'. The compustat was conceived as a means of pushing diatom morphology to match any preconception we might have. It would work by visually scanning all diatoms in a small growth chamber with a digital camera attached to a motorized microscope, and matching the observed patterns [24] against an ideal 'template'. Those diatoms that were furthest from the ideal would be destroyed with a laser or UV microbeam and the rest subjected to mutagenesis. Hopefully someone will soon build a compustat.

Diatom nanotechnology

Most fabrication techniques in nanotechnology involve planar lithographic approaches [25]. Three dimensional structures are built up plane by plane, and excruciating acrobatics are required to etch away undercuts and cavities. Diatoms build directly in 3D, which is why they

with exponential growth in numbers (at one cell division per day), any number of parts we want could be made.

The first artificial diatom patterns were synthesized by 3D vapor deposition of silica by Max Schultze back in 1863 (his plates are reproduced in [17,18]), and the feat has only been partially attempted since [27]. If silica is 'merely' precipitated onto an already existing scaffold (prepattern), as some would hypothesize, then we ought to be able to construct artificial scaffolds for silica precipitation. The physical chemistry of unassisted silica precipitation is well understood [28].

The most remarkable invention in the new field of diatom nanotechnology is that akin to the replicator [29] in the science fiction television and movie series Star Trek. Diatom shells are placed in an atmosphere of magnesium gas at 900°C for 4 hr. Apparently an atom for atom substitution of magnesium for silicon occurs, with no change in 3D shape. Thus silicon oxide, a material of limited usefulness in nanotechnology, is transformed into magnesium oxide [30]. The authors list nine other 'shape preserving gas/solid reactions' that are thermodynamically favored, and should 'replicate' diatom silica shells into a variety of oxides. The list of uses envisaged includes microcapsules for medications, water filters (sieves), catalytic substrates, sensors, optical diffraction gratings and actuators, or templates for any of these.

As mentioned, diatoms have a peculiar, silica-dependent mechanism for DNA synthesis [21,31]. This permits silica starvation synchrony to be achieved [32], by growing the diatoms in Teflon beakers to prevent them from extracting silica from glass. If pennate diatoms were then killed in mid-formation of their shells, we could produce massive quantities of nanoscale combs, such as are used in comb activators [33]. These could be sorted by size using light scattering in a FACS machine (fluorescence activated cell sorter).

Other sources of nanoscale silica objects, although not in such great variety, are the silica bodies found in grasses (Fig. 1d) [34]. One could imagine crops such as wheat being 'genetically engineered' and harvested not only for their seed but also for the silica bodies in their straw. Other, more esoteric organisms that precipitate silica include the radiolarians [35], sponges [36] and other algae [37–39].

The future

Diatom nanotechnology, conceived as an industrial process, started only as a suggestion in 1988 [40]. It is now a highly interdisciplinary, fast moving area, possibly headed for making a major contribution to nanotechnology. Biology as a source of nanotechnology has a few major advantages: large numbers of components are available via the exponential reproduction of the organisms that produce them, and mutation permits us to selectively evolve organisms with the components we want. In the course of pushing organisms to manufacture what we want them to, we are also likely to learn much about whether or not evolution is constrained. Thus bionanotechnology, although driven as an industrial pursuit, might nevertheless make fundamental contributions to our

References

- Werner, D. ed. (1977) *The Biology of Diatoms*, Blackwell Scientific Publications, Oxford
- Gordon, R. and Drum, R.W. (1970) A capillarity mechanism for diatom gliding locomotion. *Proc. Natl. Acad. Sci. U. S. A.* 67, 338–344
- Gordon, R. (1987) A retaliatory role for algal projectiles, with implications for the mechanochemistry of diatom gliding motility. *J. Theor. Biol.* 126, 419–436
- Poulsen, N.C. *et al.* (1999) Diatom gliding is the result of an actin-myosin motility system. *Cell Motil. Cytoskeleton* 44, 23–33
- Wolgemuth, C. *et al.* (2002) How myxobacteria glide. *Curr. Biol.* 12, 369–3776
- Hoiczky, E. and Baumeister, W. (1998) The junctional pore complex, a prokaryotic secretion organelle, is the molecular motor underlying gliding motility in cyanobacteria. *Curr. Biol.* 8, 1161–1168
- Higgins, M.J. *et al.* (2002) Characterization of the adhesive mucilages secreted by live diatom cells using atomic force microscopy. *Protist* 153, 25–38
- Wang, Y. *et al.* (2000) Extracellular matrix assembly in diatoms (Bacillariophyceae). IV. Ultrastructure of *Achnanthes longpipes* and *Cymbella cistula* as revealed by high-pressure freezing/freeze substitution and cryo-field emission scanning electron microscopy. *J. Phycol.* 36, 367–378
- Cohn, S.A. *et al.* (1999) High energy irradiation at the leading tip of moving diatoms causes a rapid change of cell direction. *Diatom Res.* 14, 193–206
- Hamm, C.E. *et al.* (2003) Architecture and material properties of diatom shells provide effective mechanical protection. *Nature* 421, 841–843
- Whitesides, G.M. *et al.* (2001) Soft lithography in biology and biochemistry. *Annu. Rev. Biomed. Eng.* 3, 335–373
- Harper, M.A. (1977) Movements. In *The Biology of Diatoms* (Werner, D., ed.), pp. 224–249, Blackwell Scientific Publications, Oxford
- Bothwell, M.L. *et al.* (1989) Evidence of dark avoidance by phototrophic periphytic diatoms in lotic systems. *J. Phycol.* 25, 85–94
- Kapinga, M.R.M. and Gordon, R. (1992) Cell motility rhythms in *Bacillaria paxillifer*. *Diatom Res.* 7, 221–225
- Rabovsky, J. (1995) Biogenic amorphous silica. *Scand. J. Work Environ. Health* 21 (Suppl 2), 108–110
- Mann, D.G. (2002) Diatoms: organism and image. In *Automatic Diatom Identification* (du Buf, H. and Bayer, M.M., eds), World Scientific, Singapore
- Gordon, R. and Drum, R.W. (1994) The chemical basis for diatom morphogenesis. *Int. Rev. Cytol.* 150, 243–372
- Gordon, R. and Drum, R.W. (1994) The chemical basis for diatom morphogenesis [addendum]. *Int. Rev. Cytol.* 150, 421–422
- Scala, S. *et al.* (2002) Genome properties of the diatom *Phaeodactylum tricornutum*. *Plant Physiol.* 129, 993–1002
- Kröger, N. *et al.* (2001) Silica-precipitating peptides from diatoms – The chemical structure of silaffin-1A from *Cylindrotheca fusiformis*. *J. Biol. Chem.* 276, 26066–26070
- Darley, W.M. and Volcani, B.E. (1969) Role of silicon in diatom metabolism. A silicon requirement for deoxyribonucleic acid synthesis in the diatom *Cylindrotheca fusiformis* Reimann and Lewin. *Exp. Cell Res.* 58, 334–342
- Hildebrand, M. *et al.* (1998) Characterization of a silicon transporter gene family in *Cylindrotheca fusiformis*: sequences, expression analysis, and identification of homologs in other diatoms. *Mol. Gen. Genet.* 260, 480–486
- Gordon, R. (1996) Computer controlled evolution of diatoms: design for a compustat. *Nova Hedw.* 112, 213–216
- du Buf, H., Bayer, M.M. eds (2002) *Automatic Diatom Identification*, World Scientific, Singapore
- Madou, M.J. (2002) *Fundamentals of Microfabrication: The Science of Miniaturization*, CRC Press, Boca Raton
- Parkinson, J. and Gordon, R. (1999) Beyond micromachining: the potential of diatoms. *Trends Biotechnol.* 17, 190–196
- Sowards, L.A. *et al.* (2001) Ordered silica nanostructure created by reaction of tetrahydroxysilane solution with peptide isolated from the diatom *C. fusiformis*. *Abstr. Am. Chem. Soc.* 221, 232–BIOT
- Bergna, H.E. ed. (1994) *The Colloid Chemistry of Silica. Papers from the Ralph K. Iler Memorial Symposium*. American Chemical Society.

- 29 Okuda, M. *et al.* (1994) *The Star Trek Encyclopedia, A Reference Guide to the Future*, Pocket Books, New York
- 30 Sandhage, K.H. *et al.* (2002) Novel, bioclastic route to self-assembled, 3D, chemically tailored meso/nanostructures: Shape-preserving reactive conversion of biosilica (diatom) microshells. *Adv. Mat.* 14, 429–433
- 31 Okita, T.W. and Volcani, B.E. (1978) Role of silicon in diatom metabolism. IX. Differential synthesis of DNA polymerases and DNA-binding proteins during silicate starvation and recovery in *Cylindrotheca fusiformis*. *Biochim. Biophys. Acta* 519, 76–86
- 32 Darley, W.M. and Volcani, B.E. (1971) Synchronized cultures: diatoms. In *Methods in Enzymology: Photosynthesis* (San Pietro, A., ed.), pp. 85–96, Academic Press, New York
- 33 Ye, W. *et al.* (1998) Optimal shape design of an electrostatic comb drive in microelectromechanical systems. *J. MEMS Sys.* 7, 16–26
- 34 Mulder, C. and Ellis, R.P. (2000) Ecological significance of South-West African grass leaf phytoliths: A climatic response of vegetation biomes to modern aridification trends. In *Grasses – Systematics and Evolution. Proceedings 2nd International Conference on the Comparative Biology of the Monocotyledons, Sydney* (Vol. 2) (Jacobs, S.W.L. and Everett, J., eds), pp. 246–256, CSIRO, Sydney
- 35 Anderson, O.R. (1983) *Radiolaria*, Springer-Verlag, New York
- 36 Drum, R.W. (1967) Carbon replicas of siliceous sponge spicules. *Science* 157, 581–582
- 37 Gaarder, K.R. *et al.* (1976) *Potamodiscus kalbei* Gerloff, an organism with siliceous scales. *Arch. Protistenk.* 118, 346–351
- 38 Sandgren, C.D. and Barlow, S.B. (1989) Siliceous scale production in chrysophyte algae. II. SEM observations regarding the effects of metabolic inhibitors on scale regeneration in laboratory population of scale-free *Synura petersenii* cells. *Nova Hedw.* 95, 27–44
- 39 Kristiansen, J. and Stoyneva, M. (1998) Silica-scaled chrysophytes in Bulgaria. *Cryptogamie: Algol.* 19, 19–28
- 40 Gordon, R. and Aguda, B.D. (1988) Diatom morphogenesis: natural fractal fabrication of a complex microstructure. In *Proceedings of the Annual International Conference of the IEEE Engineering in Medicine and Biology Society, Part 1/4: Cardiology and Imaging, 4–7 Nov. 1988, New Orleans, LA, USA* (Vol. 10) (Harris, G. and Walker, C., eds), pp. 273–274, Institute of Electrical and Electronics Engineers, New York
- 41 Parkinson, J. *et al.* (1999) Centric diatom morphogenesis: a model based on a DLA algorithm investigating the potential role of microtubules. *Biochim Biophys Acta* 1452, 89–102

0167-7799/03/\$ - see front matter © 2003 Elsevier Ltd. All rights reserved.
doi:10.1016/S0167-7799(03)00169-0

Putting some spine into alternative splicing

Bernard Khoo, Scott A. Akker and Shern L. Chew

Department of Endocrinology, St Bartholomew's Hospital, London, UK EC1A 7BE

Spinal muscular atrophy is a neurodegenerative disease caused by mutations of the *SMN1* gene. The homologous *SMN2* gene is unable to complement *SMN1* because of a crucial mutation in an exonic splicing enhancer, leading to alternative splicing and exclusion of exon 7. Two recent papers show that the defect in splicing of exon 7 of *SMN2* is specifically corrected by small synthetic effectors. These new and specific approaches have potential in the treatment of diseases caused by defective splicing.

Spinal muscular atrophy (SMA) is a degenerative disease of the motor nuclei in the spinal cord anterior horn and the lower brainstem. SMA presents in childhood with muscle weakness and, at the more severe end of the scale, fatal respiratory failure. Mutations of the *Survival of motor neurone* (*SMN*) locus on chromosome 5q13 are responsible for the disease. In humans, this locus contains an inverted duplication containing the telomeric *SMN1* gene and the centromeric, highly homologous *SMN2* gene. In SMA, there are missense, nonsense and splicing mutations in *SMN1*, which disrupt the protein [1]. *SMN* protein is ubiquitously found in all cell types. It is localized in subnuclear complexes known as 'gems', which are involved in small nuclear ribonucleoprotein assembly and recycling [2]. These 'gems', which can be visualized using immunofluorescence staining with *SMN* antisera, are absent in cells isolated from patients with SMA.

In mice, total deficiency of *SMN* by knockout of the orthologue causes embryonic lethality. In SMA, there is only a partial deficiency of *SMN* protein – the mutation of *SMN1* is partially complemented by *SMN2*, which is also transcribed. *SMN2* differs from *SMN1* by five nucleotides, which are translationally silent [3]. A cytosine to thymidine mutation at position +6 in exon 7 causes alternative splicing, by disrupting an exonic splicing enhancer (ESE)




Fig. 1. Defective splicing in *SMN2*. The telomeric *SMN1* is spliced correctly with exon 7 included. Full-length *SMN* protein is generated, which is localised in subnuclear 'gems'. The centromeric *SMN2*, owing to the C-to-T mutation in exon 7 is spliced alternatively. A minority of *SMN2* transcripts, indicated by the dotted arrow, are spliced and translated to the full-length *SMN* protein. The majority of *SMN2* transcripts skip exon 7 to generate *SMN17*. The truncated product derived